

12" LOC SEAM / LOC SEAM 360 PANEL SPECIFICATIONS

1. PRODUCT NAME

AMS Loc Seam panel for roof applications.

2. MANUFACTURER

ARCHITECTURAL METAL SYSTEMS

1150 State Docks Road
Eufaula, Alabama 36027
Phone: (334) 687-2032

3. PRODUCT DESCRIPTION

These standing seam roof panels offer a flat profile, with minor striations and optional pencil ribs, for an attractive appearance on higher pitched roofs. Loc Seam panels are seamed electrically and Loc Seam 360 panels have full 360 degree rolled seams formed with an electrical seaming machine. Minimum roof slope for the Loc Seam/Loc Seam 360 roof panels is ¼ to 12.

Basic Use: A roof covering system for new or retrofit construction.

Materials: Loc Seam panels are available in 24 or 22 gage 50,000 psi in either G90 zinc-coated (galvanized) steel or aluminum-zinc alloy-coated (AZ50 or AZ55) steel. Pre-painted panels have Architectural Metal Systems' SmartKote (Kynar 500®) Finish.

Panel clips for the Loc Seam panels are two part assemblies. The tab portions are a nominal 2-3/8" or 3-1/8" (for thermal blocks) in height and 3" in width, die formed 24 gage aluminum coated steel. The bases are die formed 18 gage zinc-coated (galvanized) steel. Expansion capability is 1-1/4". Loc Seam panel sidelaps have factory applied mastic, SikaLastomer-511 or equal. Its composition is 85% solids by weight. Service temperature range is -60°F to + 220° F.

Endlaps, roof flashing laps, ridges, and eave closures are sealed with tape mastic, Sika Sika-Tape TC-95 or equal. The material is non-staining, non-corrosive, non-toxic and non-volatile. Composition is 100% solid isobutylene tripolymer tape. Service temperature is -60°F to + 212° F.

Caulk: Eaves, ridge and eave closures are sealed with non-skinning butyl caulk, SikaLastomer-511 or equal. Its composition is 85% solids by weight. Service temperature range is -60°F to 220°F. All gutter and downspout joints, and roof accessories are sealed with polyurethane caulk, Sika, SikaFlex 219LM or equal. It meets or exceeds Federal specification TT-S-00230C, Type II, Class A.

All fasteners for panel to secondary framing and panel to panel will be one of the following EPDM washer head screws.

A. Premium roof fasteners shall be No. 14 x 1" self-drilling carbon steel screws with a molded zinc alloy hex washer head. Premium roof fasteners will be on all warranted roofs and all pre-finished roofs.

B. Standard roof fasteners shall be No. 14 x 1" self-drilling carbon steel screws with an integral hex washer head. Standard roof fasteners shall have a corrosive resistant coating over zinc plating. Standard roof fasteners shall be on unwarranted aluminum-zinc alloy-coated roofs only.

Loc Seam panel clips are attached to the purlins with self-drilling carbon steel screws No. 12 x 1-1/4" hex head, cadmium or zinc plated.

Maximum insulation thickness allowed with these panels is 4" without thermal blocks and 6" with thermal blocks and tall clips.

4. TECHNICAL DATA

The Loc Seam 360 panel has received a Class 90 Wind Uplift rating by Underwriters Laboratories when tested in accordance with test procedure UL 580. The Loc Seam 360 roof panel has been Factory Mutual and Miami-Dade County approved and also tested in accordance with Wind Uplift ASTM E1592 and CEGS 07416. This panel has been tested in accordance with Air Infiltration, ASTM E1680 and Water Penetration, ASTM E1646. This panel has been approved for SREF (SSTD-97) Impact Testing. This panel has received a Class A fire rating when tested in accordance with test procedure ASTM E108. The Loc Seam panel has received a Class 90 Wind Uplift rating by Underwriters Laboratories when tested in accordance with test procedure UL 580. The Loc Seam roof panel has been tested in accordance with CEGS 07416. This panel has also been tested in accordance with Air Infiltration, ASTM E1680, ASTM E283 and Water Penetration, ASTM E1646, ASTM E331. This panel has received a Class A fire rating when tested in accordance with test procedure ASTM E108.

5. INSTALLATION

Panels are joined at the sidelap with an interlocking seam. Panel sidelaps are seamed by a special electrical seaming machine. Sidelap sealer is factory applied. Roof systems Roofers. Installation may be incorporated with a light gage structural system.

6. AVAILABILITY

For availability, contact:

ARCHITECTURAL METAL SYSTEMS

7. WARRANTY

Thirty-five year material and twenty year weathertightness warranties are available.

....continued

12" LOC SEAM / LOC SEAM 360 PANEL SPECIFICATIONS

8. MAINTENANCE

Only normal routine maintenance is required over the life of the panels.

9. TECHNICAL SERVICES

For information, contact:


ARCHITECTURAL METAL SYSTEMS

10. PRODUCT NOTES

A certain amount of waviness called "oilcanning" may exist in this panel. Minor waviness of the panel is not sufficient

cause for rejection, because oilcanning does not affect the structural integrity of the panel.

Loc Seam Panels in general are known for their tendency to rumble in high winds if insulation is not used. An insulation spacer strip (FS-1) should be used along the roof purlins whenever insulation is not required in the roof system. Architectural Metal Systems reserves the right to revise all standard specifications and information. Architectural Metal Systems regularly updates its published "Standard Specifications" on the Architectural Metal Systems web site, www.ametalsystems.com, which supercede and replace any previously published standard specifications of Architectural Metal Systems.



Engineering Properties of Architectural Metal Systems 12" LocSeam Panel											
Designated Gage of Steel	Steel Yield KSI	Base Metal Thick. (In.)	Total Thick. (In.)	Panel Weight (lbs. / ft. ²)	Top In Compression			Bottom In Compression			Fb KSI
					Ix (in. ⁴ / ft.)	Sx (in. ³ / ft.)	Ma K-IN.	Ix (in. ⁴ / ft.)	Sx (in. ³ / ft.)	Ma K-IN.	
24 Ga.	50	0.0225	0.0241	1.47	0.204	0.130	3.90	0.098	0.081	2.43	30
22 Ga.	50	0.0300	0.0316	1.93	0.281	0.182	5.46	0.146	0.125	3.75	30
Gage of Panel	No. of Spans	Load Type	Maximum Total Uniform Load in PSF								
			Span Lengths, Ft.								
			1.50	2.00	2.50	3.00	3.50	4.00	4.50	5.00	
24 Ga.	1	POS	902	557	375	268	201	156	124	101	
	2	POS	611	367	243	172	128	99	78	64	
	3	POS	720	441	296	211	157	122	97	79	
	4	POS	686	418	278	198	148	114	91	74	
22 Ga.	1	POS	1365	821	544	385	287	221	176	143	
	2	POS	975	578	380	268	199	153	121	99	
	3	POS	1161	701	465	330	246	190	151	123	
	4	POS	1102	661	438	310	230	178	141	115	

Engineering Properties of Architectural Metal Systems 12" LocSeam 360 Panel											
Designated Gage of Steel	Steel Yield KSI	Base Metal Thick. (In.)	Total Thick. (In.)	Panel Weight (lbs. / ft. ²)	Top In Compression			Bottom In Compression			Fb KSI
					Ix (in. ⁴ / ft.)	Sx (in. ³ / ft.)	Ma K-IN.	Ix (in. ⁴ / ft.)	Sx (in. ³ / ft.)	Ma K-IN.	
24 Ga.	50	0.0225	0.0241	1.47	0.176	0.103	3.09	0.084	0.074	2.22	30
22 Ga.	50	0.0300	0.0316	1.93	0.242	0.150	4.50	0.126	0.112	3.36	30
Gage of Panel	No. of Spans	Load Type	Maximum Total Uniform Load in PSF								
			Span Lengths, Ft.								
			1.50	2.00	2.50	3.00	3.50	4.00	4.50	5.00	
24 Ga.	1	POS	811	479	314	221	164	126	100	81	
	2	POS	595	349	228	160	118	91	72	59	
	3	POS	716	426	280	198	147	113	90	73	
	4	POS	677	401	263	185	137	106	84	68	
22 Ga.	1	POS	1225	714	465	326	241	185	147	119	
	2	POS	924	536	348	244	180	138	110	89	
	3	POS	1121	658	430	302	224	172	137	111	
	4	POS	1058	619	404	283	209	161	128	104	

- The panels were checked for bending, shear, combined bending and shear and deflection. Deflection was limited to span/150
- Section Properties have been calculated in accordance with the 2001 North American Specification for the Design of Cold-Formed Steel Structural Members.
- Minimum yield strength of 24 and 22 gage steel is 50,000 psi.
- Steel panels are either aluminum-zinc alloy or G-90 coated. The base metal thickness was used in determining section properties.
- Positive load (POS) is applied inward toward the panel supports and is applied to the outer surface of the full panel cross-section.